

**PYROPHYLLITE LUMPS ( PQ ) AR**

**CHEMICAL ANALYSIS REPORT**

Alumina	Al <sub>2</sub> O <sub>3</sub>	20%
Silica	SiO <sub>2</sub>	73%
Ferric Oxide	Fe <sub>2</sub> O <sub>3</sub>	0.24%
Titanium	TiO <sub>2</sub>	0.23%
Magnesia	MgO	0.06%
Calcium Oxide	CaO	0.09%
K <sub>2</sub> O		0.35%
Na <sub>2</sub> O		0.88%
Loss on ignition		4%

**PHYSICAL PROPERTIES**

Color ( Raw Lumps )	White
Loose Lumps size ( Inches )	2``-8``
Hardness	2.50
Specific Gravity	2.65